

# Z258

## FKM 98 BLACK

Update 26 March 2019

### General Application Temperature Range

From -20°C  
To 220°C

### General Environmental Application

Chemicals  
Hydrocarbons  
High Temperatures  
---  
---

### Compliances

### Composition – IMDS Data

CAS n°	Qty %

### Note

...

### Disclaimer

Temperatures, applications and indications here above are meant as basic suggestions and valid for static applications with no other specific media and or conditions.

### PHYSICAL AND MECHANICAL PROPERTIES

Property	Test STD	Unit	Value
Density	ASTM D297	g/cm <sup>3</sup>	1,88 ± 0,03
Hardness	ASTM D2240	ShA	98 +0 -3
Tensile Strength	ASTM D412C	N/mm <sup>2</sup>	14,5
Elongation	ASTM D412C	%	100
Tear resistance		N/mm	
TR 10	ASTM D1329	°C	-17
Brittle Point		°C	
C. Set 24h @200°C	ASTM D395B	%	16
C. Set 70h @200°C		%	

### AGEING PROPERTIES

Environment	Test STD	Unit	Value
Air 70h @200°C	<i>Hardness Change</i>	ShA	
	<i>Tensile Strength</i>	%	
	<i>Elongation</i>	%	
	<i>Volume</i>	%	
	<i>Weight</i>	%	
	Air 70h @250°C	ASTM D573	
<i>Hardness Change</i>		ShA	+2
<i>Tensile Strength</i>		%	-4
<i>Elongation</i>		%	-11
<i>Volume</i>		%	
<i>Weight</i>		%	
Oil ASTM 3 70h @150°C	<i>Hardness Change</i>	ShA	
	<i>Tensile Strength</i>	%	
	<i>Elongation</i>	%	
	<i>Volume</i>	%	
	<i>Weight</i>	%	
	Fuel ASTM C 70h @23°C	ASTM D471	
<i>Hardness Change</i>		ShA	-3,5
<i>Tensile Strength</i>		%	
<i>Elongation</i>		%	
<i>Volume</i>		%	3,6
<i>Weight</i>		%	

