

# Z408

## FKM 70 GREEN

### RAL 6021

Update 26 March 2019

#### General Application

#### Temperature Range

From -20°C  
To 220°C

#### General Environmental Application

Chemicals  
Hydrocarbons  
High Temperatures  
---  
---

#### Compliances

#### Composition – IMDS Data

CAS n°	Qty %
9011-17-0	55-65
100402-91-3	9-14
1309-48-4	2-5
7727-43-7	9-14
1308-38-9	2-5
n.a.	3-6

#### Note

...

#### Disclaimer

Temperatures, applications and indications here above are meant as basic suggestions and valid for static applications with no other specific media and or conditions.

#### PHYSICAL AND MECHANICAL PROPERTIES

Property	Test STD	Unit	Value
Density	ASTM D297	g/cm <sup>3</sup>	2,13 ± 0,03
Hardness	ASTM D2240	ShA	70 ± 5
Tensile Strength	ASTM D412C	N/mm <sup>2</sup>	12
Elongation	ASTM D412C	%	190
Tear resistance	ASTM D624B	N/mm	34
TR 10	ASTM D1329	°C	-17
Brittle Point		°C	
C. Set 24h @200°C	ASTM D395B	%	14
C. Set 70h @200°C		%	

#### AGEING PROPERTIES

Environment	Test STD	Unit	Value
Air 70h @200°C	<i>Hardness Change</i>	ShA	
	<i>Tensile Strength</i>	%	
	<i>Elongation</i>	%	
	<i>Volume</i>	%	
	<i>Weight</i>	%	
Air 70h @250°C	ASTM D573		
	<i>Hardness Change</i>	ShA	+3
	<i>Tensile Strength</i>	%	+2
	<i>Elongation</i>	%	-18
	<i>Volume</i>	%	
Oil ASTM 3 70h @150°C	<i>Hardness Change</i>	ShA	
	<i>Tensile Strength</i>	%	
	<i>Elongation</i>	%	
	<i>Volume</i>	%	
	<i>Weight</i>	%	
Fuel ASTM C 70h @23°C	ASTM D471		
	<i>Hardness Change</i>	ShA	-4
	<i>Tensile Strength</i>	%	
	<i>Elongation</i>	%	
	<i>Volume</i>	%	+4,5
<i>Weight</i>	%		

